

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C09D 11/00, 17/00, B01F 17/00	A1	(11) International Publication Number: WO 00/20520 (43) International Publication Date: 13 April 2000 (13.04.00)
(21) International Application Number: PCT/US99/23193 (22) International Filing Date: 5 October 1999 (05.10.99) (30) Priority Data: 60/103,194 6 October 1998 (06.10.98) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: FRYD, Michael; 50 East Maple Avenue, Moorestown, NJ 08057 (US). VISSCHER, Karyn, B.; 2903 Hamilton Drive, Voorhees, NJ 08043 (US). (74) Agent: TESSARI, Joseph, A.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AE, AL, AU, BA, BB, BG, BR, CA, CN, CR, CU, CZ, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, UZ, VN, YU, ZA, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: DISPERSIONS HAVING IMPROVED STABILITY (57) Abstract Dispersion containing a liquid vehicle (which can be aqueous, semi-aqueous or non-aqueous), organic or inorganic particles (or mixtures) that are insoluble in the liquid vehicle and a polymeric dispersant, preferably a structured polymeric dispersant, having one or more segments soluble in the liquid vehicle and one or more segments insoluble in the liquid vehicle have improved stability when the insoluble segment(s) contains cross-linking groups which are cross-linked to a cross-linking compound such as itself or a polyfunctional monomer, oligomer or polymer to form an encapsulation network that entraps the particles and are particularly useful for paints or inks in coating and printing applications.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DISPERSIONS HAVING IMPROVED STABILITY

Background Of The Invention

5 This invention relates to dispersions of particles in a liquid vehicle and, more particularly, to dispersions in which the particles are entangled in a cross-linked polymer matrix.

10 Dispersions of particles in a liquid vehicle are commonly used in a wide variety of industries and processes, such as coatings (e.g., paint and ink), magnetic or optical recording media (e.g., tapes and disks), cosmetics (e.g., lipsticks and nail polish); agriculture (e.g., insecticides), pharmaceutical preparations and many others. In addition, in a concentrated form (such as can be obtained by centrifugation followed by decanting the supernatant liquid) the dispersions are useful for tinting, coloring fibers, coloring molded resins, for adding pigment to
15 flexographic plates and a variety of other applications.

As expected, these dispersions are very diverse. Generally speaking, however, these dispersions all contain a liquid vehicle (such as water, an organic solvent, or a combination of the two) and some type of particle (such as a pigment, a
20 pharmaceutically active compound, metallic flakes, hollow glass spheres, discrete polymer particles, etc.). Typically, but not always, a dispersant is used to help maintain the particles in a suspended state in the liquid vehicle; i.e., prevent the particles from settling out of the liquid. In many instances, the dispersant used is a polymer.

25 There has been significant effort in the art directed at improving the stability of the dispersions so that the particles are less likely to settle out of the liquid under a defined set of conditions. The reason for the effort is that a dispersion with improved stability can translate into products having a longer shelf life; products
30 that can survive more rigorous storage conditions (e.g., extreme temperature cycles); products that are easier or less expensive to transport or handle during use; and products that are more uniform and consistent in quality, and products that offer greater formulation latitude.

35 The effort to improve dispersion stability to date have included improvements in the processes used to make the dispersions, the development of new dispersants and the exploration of the interaction between dispersants and particular liquid

vehicle formulations. Recently, there has been a good deal of research directed at modifying the particles, especially the particle surface, in order to improve the dispersion stability. For instance, recent advances in the art have seen the advent of coated particles, particles whose surfaces have been chemically modified, and
5 particles that are covalently bonded to a dispersant.

While much of the effort has had general application at improving dispersion stability, some of that effort has not found utility in particular applications. For example, pigment dispersions used in ink jet printing applications have very
10 unique and demanding requirements. Ink jet printing is a non-impact and non-contact printing process in which an electronic signal produces droplets of ink that are deposited on a wide variety of substrates such as paper, transparent film, plastics, metals and fabrics. Typically, the ink is ejected from a printhead containing a plurality of very small nozzles using thermal or piezoelectric ejection
15 technology. In ink jet printing, it is critical that the ink components remain stable, not only in storage but also over repeated firing cycles; that they not interact with the components used to manufacture the printhead; that they not clog the nozzle openings; and that they not form a film on the orifice plate or resistors used in the printhead. In addition, because such printing is often used in an office
20 environment, such inks tend to be aqueous based dispersions.

Summary Of The Invention

In the broadest sense, the present invention provides a dispersion of particles in a liquid vehicle, comprising:

- 25 (a) a liquid vehicle selected from the group consisting of water, organic solvents and combinations thereof;
- (b) particles that are at least substantially insoluble in the liquid vehicle;
- (c) a polymer dispersant having at least one segment soluble in the liquid vehicle and at least one segment insoluble in the liquid vehicle,
- 30 (d) wherein said at least one insoluble segment has cross-linking moieties that are cross-linked to at least one cross-linkable component which is at least substantially insoluble in the liquid medium and is selected from the group consisting of itself, a polyfunctional monomer, a polyfunctional oligomer, and a polyfunctional polymer to form an
35 encapsulation network which entraps the particles.

In further embodiments, the dispersion may also contain a catalyst to facilitate the cross-linking reaction. The particles may be organic or inorganic and the particles may or may not be covalently bonded to the dispersant.

5 **Brief Description of the Drawings**

Figure 1 is a schematic illustration of the natural orientation of a graft copolymer having soluble and insoluble segments and an insoluble particle in a liquid medium.

- 10 Figure 2 is a schematic illustration of an entrapped particle in the dispersions of the present invention, particularly illustrating the cross-linked insoluble segment of the polymer (in this instance a graft copolymer).

Detailed Description Of The Embodiments

- 15 The dispersions of this invention essentially comprise a liquid vehicle, particles and a dispersant polymer that has been cross-linked to entrap the particles. In further embodiments the dispersion may contain a cross-linking component and catalysts. Depending on the ultimate use of the dispersions, various additives and adjuvants may be used in the dispersion as is common in the particular application
20 of interest.

Liquid Vehicle

- The liquid vehicle, while an essential component of the invention, may be aqueous or non-aqueous and may contain water, organic solvents or combinations
25 thereof. The particular type and amount of liquid will be readily determined by the particular end use of the dispersions. For example, the paint industry utilizes both solvent based and aqueous based paints, stains and coatings. In ink jet ink applications, the vehicle typically comprises a mixture of water and at least one water soluble organic solvent, most commonly a pyrrolidone or a polyhydric
30 alcohol, or both. Generally speaking, there is a strong preference (for environmental, cost and health and safety reasons) to utilize aqueous based dispersions wherever possible. Accordingly, an aqueous based liquid vehicle (i.e., a liquid vehicle comprising at least 50% by weight of water) is a preferred embodiment of the present invention.

Particles

Although particles are required for the invention, the type and composition of the particles is not particularly critical and will largely depend upon the ultimate end use application of the dispersion. By definition, the particles are at least
5 substantially insoluble in the liquid vehicle. If they were soluble, the resulting mixture would be a solution rather than a dispersion. Apart from that general limitation, the particles may be organic, inorganic or mixtures thereof. Examples of suitable particles include pigments, insoluble dyes, metallic particles, biologically active compounds, pharmaceutically active compounds, polymer
10 particles, hollow glass spheres, etc.

The particle size can have an effect on dispersion stability. In general, smaller particles tend to create more stable dispersions in that Brownian motion helps to prevent the particles from flocculating or settling. Small particle size pigments
15 also produce maximum color strength and there fore may be desirable in applications using pigment dispersions. The particle size will vary substantially depending upon the desired end use for the dispersion. For ink jet ink applications, for example, a useful particle size will be in the range of 0.005 to 15 microns. For paints, the particle size may be as high as 75 to 100 microns and in
20 other coatings the particles may be up to several hundred microns. One of ordinary skill in the art can readily determine the appropriate particle size for the desired application.

Fine particles of metal (such as copper, iron, steel, aluminum and alloys) or metal
25 oxides (e.g., silica, alumina, titania) may be used to practice the invention. For example, metal and metal oxides are suitable for the preparation of magnetic and/or optical recording media. In addition, some coating applications might utilize metallic flakes in combination with pigments to provide a "pearl-like" finish.

30 The amount of particles used in the dispersion is not critical to the invention and can be as desired for the end use application. For instance, paints, inks and cosmetics may require significantly greater particle concentrations on a weight basis compared to dispersions of highly reactive pharmaceutical or agricultural
35 compounds. In a preferred embodiment, the particles comprise pigments.

Polymer Dispersant:

The function of the polymeric dispersant is to disperse the insoluble particles in the liquid vehicle. Structured polymers are particularly preferred. The term "structured polymer" means any polymer that does not have a random structure.

- 5 Stated differently, the term "structured polymer" means that the polymer has identifiable and defined segments or areas based on the type, identity and/or behavior of the monomers contained within the segment or area. Typically, but not always, those segments are characterized as being hydrophobic or hydrophilic.
- 10 Examples of structured polymers include block polymers, graft polymers, tapered polymers and branch polymers. Particularly preferred structured polymeric dispersants for use in the present invention are block and graft copolymers. Structured polymers are particularly preferred because it is easier to produce segments having the desired functionality in such polymers versus random
- 15 polymers. Graft polymers having an insoluble backbone and soluble arms are particularly preferred. Such polymers can be prepared by techniques well known in the art. For example, block polymers can be made using the well known Group Transfer Polymerization technique and graft polymers may be prepared using chain transfer agents. Specific conditions for preparing particularly preferred
- 20 polymers are set forth in the examples.

Regardless of the structure of the polymer dispersant, it must contain one or more segments that are soluble in the liquid vehicle and one or more segments that are insoluble in the vehicle. As such, the polymer has an area or segment that has an

25 affinity for the liquid vehicle and an area or segment that has an aversion for the liquid vehicle. When the polymer is placed into the liquid, it will naturally tend to orient itself such that the segment(s) with aversion to the liquid is/are clustered together to form a liquid adverse "core" and the segment(s) with affinity for the vehicle are aligned away from the core. The particles, which are insoluble and

30 thus also have an aversion for the liquid, tend to migrate into the "core" formed by the polymer alignment. This is illustrated schematically in Figure 1, where 10 is a particle disposed within a core 12 formed by the natural orientation of the polymer 14 (in this instance an graft copolymer) having a soluble arms 16, 16 and an insoluble backbone 18.

35

Generally speaking, the insoluble particle is relatively content to stay isolated in this liquid free "core". Under certain conditions, however, such as changes in

temperature, changes in composition of the liquid vehicle, etc. the particles tend to move out of the core where they can flocculate and precipitate. The present invention addresses this problem by cross-linking the insoluble polymer segment to form a network or matrix around the particle which is extremely resistant to changes in liquid vehicle composition, temperature and other factors known to destabilize dispersions. As seen in Figure 2, the particle 20 is entrapped in a network formed by the insoluble polymer segment 22 and the cross-linking bonds 24. The cross-linking bonds 24 are very stable and effectively prevent the particle from leaving the "core" formed by the polymer. As in Figure 1, the soluble segment of the polymer 26 remains aligned into the liquid vehicle and away from the liquid adverse "core". As can be appreciated from viewing Figure 2, it is not necessary that the particle 20 be covalently bonded to the polymer dispersant to obtain the improved dispersion stability. However, although not illustrated, it is understood that the dispersions of the present invention do not preclude situations where the particle, in addition to being entrapped in the cross-linked matrix, would also be covalently bonded to the polymer.

The monomer composition of the soluble segment and the insoluble segment of the dispersant will, of course, depend upon the liquid vehicle selected for the dispersion. If an aqueous vehicle is selected, the soluble segment will contain hydrophilic monomers and the insoluble segment will contain hydrophobic monomers. If a non-aqueous vehicle (that is, one containing primarily organic solvents) is selected, the opposite would be true. Therefore, for ease of reference, the useful monomers can be classified generally as hydrophobic or hydrophilic and will be so categorized herein. It is also possible to introduce solubility by making a salt of the monomers used in the soluble segment, particularly for aqueous dispersions, as is known in the art. Whatever the precise composition of the soluble segment may be, it is important that this segment be such that the entire polymer dispersant (or a salt thereof) is soluble in the liquid vehicle.

Hydrophobic and hydrophilic monomers are well known to those skilled in the art. Particularly useful hydrophobic monomers (which are soluble in a non-aqueous vehicle) include:


- 1) alkyl, aryl, and alkyl aryl acrylates or methacrylates having 1-12 carbon atoms in the alkyl group and/or 6-12 carbons in the aryl group such as methyl, ethyl, butyl, propyl, isobutyl, hexyl 2-ethyl hexyl,

nonyl, lauryl, isobornyl, benzyl acrylates and methacrylates and the like;

2) polymerizable vinyl aromatic monomers such as styrene, alpha methyl styrene, vinyl toluene and the like; and

5 3) aliphatic hydrocarbon monomers such as isoprene and butadiene.

Particularly useful hydrophilic monomers (i.e., those which can impart water-solubility) include: (1) acid monomers such as acrylic acid, methacrylic acid, acrylamidomethylpropane sulfonic acid, itaconic acid, maleic acid and styrene
10 sulfonic acid; (2) amine-containing monomers such as 2-dimethylaminoethyl methacrylate, 2-dimethylaminoethyl acrylate, 2-diethylaminoethyl methacrylate, and 2-diethylaminoethyl acrylate; and (3) monomers having oligoether moieties of the general formula:



15 wherein R = H or methyl; R₁ = alkyl of 1 to 4 carbon atoms, aryl of 6 to 12 carbon atoms, or alkyl-aryl, and n = 1 to 20, examples of which include ethoxyethyl methacrylate, butoxyethyl methacrylate, ethoxytriethylene methacrylate, methoxy-polyethylene glycol methacrylate, and 2-ethoxytriethylene glycol methacrylate.

20 It may be necessary to neutralize the monomers to make them soluble. Suitable reagents to neutralize the acid monomers include mono-, di-, tri-methylamine, morpholine, n-methyl morpholine; alcohol amines such as dimethylethanolamine (DMEA), methyldiethanolamine, mono-, di-, and tri-ethanolamine; pyridine; ammonium hydroxide; tetra-alkylammonium salts such as tetramethylammonium
25 hydroxide, tetraethyl- ammonium hydroxide; alkali metals hydroxides such as lithium, sodium and potassium hydroxide, aminopropanol, etc. The amine monomers may be neutralized with inorganic and organic acid such as acetic acid, formic acid, oxalic acid, dimethylol propionic acid, hydrochloric acid, p-toluene sulfonic acid, benzene sulfonic acid, nitric acid, citric acid, and the like; halogens
30 such as chloride, fluoride, and bromide, and inorganic acids, such as sulfuric acid, nitric acid, phosphoric acid and the like. It is also possible to convert the amino group into a tetra-alkyl ammonium salt. Alternatively, the amine functionalities can be rendered water-soluble by quaternization with reagents such as benzyl chloride, dimethylsulfate, methyl chloride, etc.

35 Depending on the number, n, of oxyethylene units in the monomers containing oligoether moieties, the polymer can be slightly or completely water soluble. The

solubility of the polymer increases as the number of oxyethylene units increases. The monomers having oligoether moieties can be advantageously used to adjust the physical properties, such as Tg, of the polymer dispersant.

- 5 In accordance with the invention, the insoluble segment(s) of the polymer have cross-linkable functional moieties. The insoluble segment(s) of the dispersant is thus capable of cross-linking to itself or to an additional cross-linking compound (e.g., monomer, oligomer, or polymer) that has suitable cross-linking functionality. Table 1 identifies suitable functional groups that may be
10 incorporated into the insoluble segment of the dispersant and the companion cross-linking group that may be present in the cross-linking compound.

TABLE 1

<u>FUNCTIONAL GROUP</u>	<u>CROSS-LINKING GROUP</u>
epoxy	amine, anhydride, acid, phenolic hydroxide, hydroxyl, N-methylol, aldehyde, acetoacetoxy
hydroxyl	isocyanate, epoxide, N-methylol, anhydride, ester
anhydride	epoxide, amine, hydroxyl
acid	epoxide, N-methylol, isocyanate
cyclic carbonate	amine
activated allyl	amine, radical initiator
amine	aldehyde, epoxide, anhydride, isocyanate, ester, acetoacetoxy, activated allyl
silane, silicate, silanol, silicone	hydroxyl, water, acid, isocyanate, silane, silicate
imine	aldehyde, epoxide, anhydride, isocyanate, ester, acetoacetoxy, activated allyl

- Particularly preferred cross-linking combinations are the epoxy moieties with
15 amines, hydroxyl moieties with isocyanates and silane moieties with themselves. As noted above, the functional group and the cross-linking group can be incorporated into the insoluble segment(s) of the polymer dispersant by selection of appropriate monomers or, preferably, a separate cross-linking compound having the appropriate group is added to the dispersion. Useful cross-linking
20 compounds are those which are insoluble in the liquid vehicle and which do not have significant reaction with the major component of the liquid vehicle. For aqueous dispersions useful cross-linking compounds include diacrylate, diisocyanate, m-tetramethylxylene diisocyanate ("m-TMXDI"), hexamethylene diisocyanate trimer ("HMDI") and isophorone diisocyanate trimer ("IPDI"). m-
25 TMXDI is particularly preferred.

The dispersions of the present invention are made in essentially the same manner as dispersions in the prior art. The particles are premixed with the selected dispersant and then charged to a suitable dispersion apparatus (e.g., a media mill, attritor, 2-roll mill, etc.) and thoroughly mixed. The cross-linking reaction then takes place and the cross-linking compound (if used) is added to the mixture. To facilitate the cross-linking reaction, it may be desirable to add a catalysts and/or to elevate the temperature of the mixture. Useful catalysts can be those that are either soluble or insoluble in the liquid and are selected depending upon the cross-linking groups. For isocyanate-hydroxy type cross-linking reactions, suitable catalysts include (for aqueous systems) dibutyltin dilaurate ("DBTDL"), tributyl amine ("TBA"), trioctyl amine, tridodecyl amine and dimethyldodecyl amine. DBTDL and TBA are particularly preferred for aqueous dispersions. For non-aqueous systems, 2,2,2-diaminobicyclooctane ("DABCO") may be used as the catalyst.

Other Ingredients

The dispersions of this invention may also contain other ingredients or additives depending on the particular end use. For example, surfactants are commonly used in coatings such as paint or inks to alter surface tension as well as maximize penetration into the substrate (for ink applications in particular). Normally, care must be taken in selecting the surfactant, however, because the surfactant can compete for the particles (i.e., pigments) and thus may destabilize the dispersion. The entrapment of the particles in accordance with the present invention, however, should permit greater latitude in selecting surfactants.

Biocides are also commonly used in dispersions to inhibit growth of microorganisms. Sequestering agents, such as EDTA, are also commonly used to eliminate deleterious effects of heavy metal impurities. Other common additives include humectants, viscosity modifiers, binders, coating aides, thickeners and the like, depending on the desired end use of the dispersion.

Examples

The invention will now be further illustrated by, but not limited to, the following examples, in which parts and percentages are by weight unless otherwise noted.

EXAMPLE 1

This Example describes the synthesis, dispersion and encapsulation of a graft copolymer with anionic hydrophilic arms, and a hydrophobic backbone.

- 5 A macromonomer was prepared by charging the following components to a 2 liter flask equipped with a thermocouple, stirrer, dropping funnels, reflux condenser, and the means for bubbling nitrogen through the reaction.

Portion 1		Parts
Methyl methacrylate monomer		140.92
Methacrylic acid monomer		61.60
Isopropanol		259.80
Portion 2		
Methylethyl ketone		8.04
Isopropanol		18.76
Isopropyl-bis(borondifluoro- dimethylglyoximate) cobaltate (III) ("DMG Co(III)") catalyst		0.02
VAZO®-52 Initiator		0.20
Portion 3		
Isopropanol		15.60
Portion 4		
DMG Co (III) Catalyst		0.04
VAZO®-52 Initiator		2.20
Methylethyl ketone		24.06
Isopropanol		56.14
Portion 5		
Methyl methacrylate monomer		90.10
Methacrylic acid monomer		92.40

- 10 Portion 1 was heated to its reflux temperature in about 15 minutes. Portion 2 was thoroughly mixed and added all at once and the composition was held at its reflux temperature for 5 minutes. The vessel which contained Portion 2 was rinsed with Portion 3, which was then added to the reaction vessel. Portions 4 and 5 were added simultaneously to the reaction vessel while the vessel maintained its reflux
- 15 temperature. For Portion 4, the first 54.8% was added over 90 minutes, and the remaining 45.2% was added over 240 minutes. For Portion 5, the first 67% was added over 120 minutes and the remaining 33% was added over an additional 120 minutes. After Portions 4 and 5 have been added to the vessel, the reaction is held at reflux for an additional 45 minutes and then cooled to room temperature.

The resulting macromonomer solution has a solids content of approximately 50%, and contained 60% methyl methacrylate and 40% methacrylic acid. This polymer has an approximate weight average molecular weight of 3100, and number average molecular weight of 2000.

5

A graft copolymer was then prepared from the macromonomer by charging the following components to a 10 liter flask equipped as above:

Portion 1	Parts
Macromonomer (prepared above)	3079.00
2-Ethylhexyl acrylate monomer	206.11
Hydroxyethyl acrylate monomer	227.81
Isopropanol	600.00
Portion 2	
tertbutylperpivalate (Lupersol®-11)	25.95
Isopropanol	75.51
Portion 3	
2-Ethylhexyl acrylate	1511.49
Hydroxyethyl acrylate	1679.59
Portion 4	
VAZO®-52 initiator	25.95
Methylethyl ketone	24.51
Isopropanol	235.05
Portion 5	
VAZO®-52 Initiator	51.90
Methylethyl ketone	62.46
Isopropanol	149.59

- 10 Portion 1 was heated to reflux temperature over a period of approximately 20 minutes. Portion 2 was mixed and charged to the reactor in two equal portions. After the first was added, the reaction was held at reflux for 10 minutes before the second half was added. After the second half of Portion 2 was added, the reaction was held at reflux for 10 minutes. Portions 3 and 4 were added simultaneously to
- 15 the reaction vessel while maintaining a reflux in the reaction vessel. Portion 3 was added over 180 minutes, and Portion 4 was added over 240 minutes. After the additions of Portions 3 and 4 were completed, Portion 5 was added to the reaction vessel over 15 minutes, maintaining the reflux temperature. After the addition of Portion 5 was completed, the reaction mixture was maintained at
- 20 reflux for 120 minutes and then cooled to room temperature.

The resulting graft copolymer solution had a solids content of approximately 63% by weight and had the following overall approximate composition: 33.25% 2-ethylhexyl acrylate; 36.75% hydroxyethyl acrylate; 18% methyl methacrylate and 12% methacrylic acid. This material had a weight average molecular weight of approximately 21,000 and a number average molecular weight of approximately 7800.

A waterborne pigment dispersion was prepared by charging the following constituents into an 01-Attritor media mill:

10

Portion 1		Parts
Graft copolymer prepared above		54.44
2-amino-2-methyl-1-propanol ("AMP")		5.31
Deionized water		237.75
Portion 2		
Quinacridone magenta pigment		52.50
Zirconia media (0.8-1.0 mm)		850.00

The graft copolymer is mixed with the neutralizing agent (AMP) and deionized water to form Portion 1. The material from Portion 1 was mixed with the materials in Portion 2 and the constituents were ground for 16 hours at 500 rpm in an 01-Attritor at 100°F. A uniform, transparent, waterborne pigment dispersion was formed that was stable and deflocculated and had a pH range of 7.5-8.5. This dispersion contains 15% pigment and 10% polymer.

This material was used in an encapsulation reaction that involves a crosslinking reaction between hydroxyl groups in the backbone and a hydrophobic diisocyanate/catalyst system.

20

Ingredient	Amount
Waterborne dispersion prepared above (10% polymer, 15% pigment)	20.00g
m-Tetramethylxylene diisocyanate crosslinker (isocyanate:OH = 0.4:1.0)	0.34 g
Dibutyltin dilaurate (100% solution)	1 drop

The above ingredients were mixed together and heated at 40-50°C, with efficient stirring, for a period of 6 hours. After this time period, the mixture is cooled to room temperature and tested for flocculation stability. Samples of both the encapsulated, and unencapsulated pigment dispersions were tested for flocculation

25

stability by adding 0.5 g of the sample to different concentrations of an incompatible vehicle, such as butyl cellosolve in water, which would flocculate the unencapsulated dispersion. The encapsulated samples were stable in much more aggressive vehicle formulations (often in 100% butyl cellosolve).

5

EXAMPLE 2

This Example describes the synthesis, dispersion and encapsulation of a graft copolymer with nonionic hydrophilic arms, and a hydrophobic backbone.

- 10 The following components were charged into a 1 liter flask equipped as above to form a graft copolymer solution:

Portion 1	Parts
Bisomer S20W (a polyethyleneglycol methacrylate, 49% solids in water, Mn = 2000, available from International Specialty Chemicals)	37.93
Hydroxyethyl acrylate	6.56
n-Butyl acrylate	5.93
Isopropanol	191.94
Portion 2	
n-Butyl acrylate	43.52
Hydroxyethyl acrylate	48.10
Bisomer S20W	278.17
Portion 3	
VAZO®-52 Initiator	1.31
Methylethyl ketone	1.24
Isopropanol	21.97
Portion 4	
VAZO®-52 initiator	2.62
Methylethyl ketone	3.15
Isopropanol	7.56

- 15 Portion 1 was heated to reflux temperature over a period of approximately 20 minutes. Portions 2 and 3 were added simultaneously to the reaction vessel while maintaining a reflux in the reaction vessel. Portion 2 was added over 180 minutes, and Portion 3 was added over 240 minutes. After the additions of Portions 2 and 3 were completed, Portion 4 was added to the reaction vessel over 15 minutes, maintaining the reflux temperature. After the addition of Portion 4
- 20 was completed, the reaction mixture was maintained at reflux for 120 minutes and then cooled to room temperature.

The resulting graft copolymer solution had a solids content of approximately 40% by weight and had the following overall approximate composition: 19% n-butyl acrylate; 21% hydroxyethyl acrylate; and 60% Bisomer S20W. This material had a weight average molecular weight of approximately 12300 and a number average molecular weight of approximately 5700.

A waterborne pigment dispersion was prepared by charging the following constituents into an 01-Attritor media mill:

Portion 1	Parts
Graft copolymer prepared above	87.98
Deionized water	209.52
Portion 2	
Quinacridone magenta pigment	52.50
Zirconia media (0.8-1.0 mm)	850.00

10

The graft copolymer is mixed with the deionized water to form Portion 1 (no neutralizing agent is needed). The material from Portion 1 was mixed with the materials in Portion 2 and the constituents were ground for 16 hours at 500 rpm in an 01-Attritor at 100°F. A uniform, transparent, waterborne pigment dispersion was formed that was stable and deflocculated and had a pH range of 2-4. This dispersion contains 15% pigment and 10% polymer.

15

This material was used in an encapsulation reaction that involves a crosslinking reaction between hydroxy groups in the backbone and a hydrophobic diisocyanate/catalyst system.

20

Ingredient	Amount
Waterborne dispersion prepared above (10% polymer, 15% pigment)	20.00 g
m-Tetramethylxylene diisocyanate crosslinker (isocyanate:OH=0.4:1.0)	0.34 g
Dibutyltin dilaurate (100% solution)	1 drop

The above constituents mixed together and heated at 40-50°C, with efficient stirring, for a period of 6 hours. After this time period, the mixture is cooled to room temperature and tested for flocculation stability. Samples of both the encapsulated and unencapsulated pigment dispersions were tested for flocculation stability as in Example 1. The encapsulated samples were stable in much more aggressive vehicle formulations compared to the unencapsulated samples.

25

EXAMPLE 3

This Examples describes the synthesis, dispersion and encapsulation of a graft copolymer with cationic hydrophilic arms, and a hydrophobic backbone.

5

The following components were charged into a 1 liter flask equipped as above to form a graft copolymer solution:

Portion 1		Parts
Dimethylaminoethyl methacrylate ("DMAEMA") macromonomer (50.6% solids; MW=8000; containing about 51 DMAEMA units)		29.60
Hydroxyethyl acrylate		18.25
2-Ethylhexyl acrylate		16.51
Isopropanol		60.88
Portion 2		
Luperisol®-11 initiator		2.08
Isopropanol		6.05
Portion 3		
2-Ethylhexyl acrylate		121.07
Hydroxyethyl acrylate		134.53
DMAEMA macromonomer		217.03
Portion 4		
VAZO®-52 initiator		2.08
Methylethyl ketone		1.96
Isopropanol		18.83
Portion 5		
VAZO®-52 initiator		4.16
Methylethyl ketone		5.00
Isopropanol		11.98

- 10 Portion 1 was heated to reflux temperature over a period of approximately 20 minutes. Portion 2 was added to Portion 1 in two equal portions 10 minutes apart. After the second half of Portion 2 has been added, the reaction is held at reflux for 10 minutes. Portions 3 and 4 were added simultaneously to the reaction vessel while maintaining a reflux. Portion 3 was added over 180 minutes, and
- 15 Portion 4 was added over 240 minutes. After the additions of Portions 3 and 4 were completed, Portion 5 was added to the reaction vessel over 15 minutes, maintaining the reflux temperature. After the addition of Portion 5 was completed, the reaction mixture was maintained at reflux for 120 minutes and then

20

The resulting graft copolymer solution had a solids content of approximately 65% by weight and had the following overall approximate composition: 33% 2-ethylhexyl acrylate; 37% hydroxyethyl acrylate; and 30% DMAEMA macromonomer. This material had a weight average molecular weight of approximately 7337 and a number average molecular weight of approximately 3252.

A waterborne pigment dispersion was prepared by charging the following constituents into an 01-Attritor media mill:

10

Portion 1		Parts
Graft copolymer prepared above		54.09
0.1N HCl water solution		243.40
Portion 2		
Quinacridone magenta pigment		52.50
Zirconia media (0.8-1.0 mm)		850.00

The graft copolymer is neutralized with the 0.1N HCl to form Portion 1. The material from Portion 1 was mixed with the materials in Portion 2 and the constituents were ground for 16 hours at 500 rpm in an 01-Attritor at 100°F. A uniform, transparent, waterborne pigment dispersion was formed that was stable and deflocculated and had a pH range of 2-4. This dispersion contains 15% pigment and 10% polymer.

This material was used in an encapsulation process involving a crosslinking reaction between hydroxyl groups in the backbone and a hydrophobic diisocyanate/catalyst system.

20

Ingredient	Amount
Waterborne dispersion prepared above (10% polymer, 15% pigment)	20.00 g
m-Tetramethylxylene diisocyanate crosslinker (isocyanate:OH=0.4:1.0)	0.28 g
Dibutyltin dilaurate (100% solution)	1 drop

The above constituents mixed together and heated at 40-50°C, with efficient stirring, for a period of 6 hours. After this time period, the mixture is cooled to room temperature and tested for flocculation stability as in Example 1. The encapsulated samples were more stable than the non-encapsulated samples.

25

EXAMPLE 4

This Example describes the synthesis, dispersion and encapsulation of a block copolymer with an anionic hydrophilic block, and a hydrophobic block.

- 5 The following components were charged into a 1 liter flask equipped as above to form a graft copolymer solution:

Portion 1	Parts
MMA/MAA macromonomer (from Example 1)	227.09
Isopropanol	60.00
Portion 2	
Luperisol®-11 initiator	0.24
Portion 3	
2-Ethylhexyl methacrylate	126.68
Hydroxyethyl methacrylate	140.01
Portion 4	
VAZO®-52 Initiator	3.08
Isopropanol	74.50

- 10 Portion 1 was placed in the reactor and heated to reflux temperature over a period of approximately 20 minutes. Portion 2 was added to Portion 1 as a single shot and the reaction was held for 5 minutes. Portions 3 and 4 were each mixed thoroughly and added simultaneously to the reaction vessel while maintaining a reflux in the reaction vessel. Portion 3 was added over 240 minutes, and Portion 4 was added over 270 minutes. After the additions of Portions 3 and 4 were
15 completed, the reaction mixture was maintained at reflux for at least 30 minutes and then cooled to room temperature.

- 20 The resulting block copolymer solution had a solids content of approximately 60% by weight and had the following overall approximate composition: 33% 2-ethylhexyl methacrylate; 36% hydroxyethyl methacrylate; 18% methyl methacrylate and 12% methacrylic acid.

A waterborne pigment dispersion was prepared by charging the following constituents into an 01-Attritor media mill:

Portion 1		Parts
Graft copolymer prepared above		58.54
AMP		7.15
Water		231.81
Portion 2		
Quinacridone magenta pigment		52.50
Zirconia media (0.8-1.0 mm)		850.00

The graft copolymer is neutralized with AMP to form Portion 1. The material from Portion 1 was mixed with the materials in Portion 2 and the constituents were ground for 16 hours at 500 rpm in an 01-Attritor at 100°F. A uniform, transparent, waterborne pigment dispersion was formed that was stable and deflocculated and had a pH range of 2-4. This dispersion contains 15% pigment and 10% polymer.

- 10 This material was then used in an encapsulation reaction involving a crosslinking reaction between hydroxyl groups in the hydrophobic block and a hydrophobic diisocyanate/catalyst system.

Ingredient	Amount
Waterborne dispersion prepared above (10% polymer, 15% pigment)	20.00 g
m-Tetramethylxylene diisocyanate crosslinker (isocyanate:OH=1.0:1.0)	0.7 g
Dibutyltin dilaurate (100% solution)	1 drop

- 15 The above constituents mixed together and heated at 40-50°C, with efficient stirring, for a period of 6 hours. After this time period, the mixture is cooled to room temperature and tested for flocculation stability as in Example 1, with the same results.

20 EXAMPLE 5

This Example describes the synthesis, dispersion and encapsulation of a random, linear copolymer containing the same portion reactive functional groups and monomers seen in Examples 1 and 4.

- 25 The following components were charged into a 1 liter flask equipped as above to form a graft copolymer solution:

Portion 1	Parts
Methylethyl ketone	200.00
2-Ethylhexyl methacrylate	31.73
Hydroxyethyl methacrylate	36.40
Methyl methacrylate	20.00
Methacrylic acid	12.04
Portion 2	
Methylethyl ketone	35.00
VAZO®-67	5.00
Portion 3	
2-Ethylhexyl methacrylate	126.90
Hydroxyethyl methacrylate	145.60
Methyl methacrylate	80.00
Methacrylic acid	48.16
Portion 4	
Methylethyl ketone VAZO®-52	65.00
VAZO®-67	10.00

Portion 1 was placed in the reactor and heated to reflux temperature over a period of approximately 20 minutes. Portion 2 was added to Portion 1 over one minute and the reaction was held for 5 minutes. Portions 3 and 4 were added simultaneously to the reaction vessel while maintaining a reflux in the reaction vessel. Portion 3 was added over 240 minutes, and Portion 4 was added over 300 minutes. After the additions of Portions 3 and 4 were completed, the reaction mixture was maintained at reflux for at least 30 minutes and then cooled to room temperature.

The resulting linear, random copolymer solution had a solids content of approximately 58% by weight and had the following overall approximate composition: 33% 2-ethylhexyl methacrylate; 36% hydroxyethyl methacrylate; 18% methyl methacrylate and 12% methacrylic acid.

A waterborne pigment dispersion was prepared by charging the following constituents into an 01-Attritor media mill:

Portion 1	Parts
Copolymer prepared above	59.96
AMP	6.98
Water	230.56
Portion 2	
Quinacridone magenta pigment	52.50
Zirconia media (0.8-1.0 mm)	850.00

The copolymer is neutralized with the AMP to form Portion 1. The material from Portion 1 was mixed with the materials in Portion 2 and the constituents were ground for 16 hours at 500 rpm in an 01-Attritor at 100°F. A uniform,
5 transparent, waterborne pigment dispersion was formed that was stable and deflocculated and had a pH range of 2-4. This dispersion contains 15% pigment and 10% polymer.

This material was used in the following encapsulation reaction.

10

Ingredient	Amount
Waterborne dispersion prepared above (10% polymer, 15% pigment)	20.00 g
m-Tetramethylxylene diisocyanate crosslinker (isocyanate:OH=1.0:1.0)	0.7 g
Dibutyltin dilaurate (100% solution)	1 drop

The above constituents mixed together and heated at 40-50°C, with efficient stirring, for a period of 6 hours. After this time period, the mixture is cooled to room temperature and tested for flocculation stability as in Example 1. The
15 encapsulated samples were more stable.

EXAMPLE 6

This Example describes the synthesis, dispersion and encapsulation of a graft copolymer with nonionic, hydrophilic arms, and a hydrophobic backbone
20 containing a glycidyl methacrylate functional group. This is an example of an encapsulation reaction using a different type of crosslinker. Nonionic, hydrophilic arms are necessary because the glycidyl methacrylate group would react with the acid groups found in the hydrophilic arms of Example 1.

25 The following components were charged into a 2 liter flask equipped as above to form a graft copolymer solution:

Portion 1		Parts
Bisomer S20W		60.35
Glycidyl methacrylate		12.15
n-Butyl acrylate		18.22
Isopropanol		440.26
Portion 2		
n-Butyl acrylate		133.63
Glycidyl methacrylate		89.09
Bisomer S20W		442.54
Portion 3		
VAZO®-52 Initiator		2.54
Methylethyl ketone		2.40
Isopropanol		23.00
Portion 4		
VAZO®-52 initiator		5.08
Methylethyl ketone		6.11
Isopropanol		14.64

Portion 1 was heated to reflux temperature over a period of approximately 20 minutes. Portions 2 and 3 were added simultaneously to the reaction vessel while maintaining a reflux in the reaction vessel. Portion 2 was added over 180 minutes, and Portion 3 was added over 240 minutes. After the additions of Portions 2 and 3 were completed, Portion 4 was thoroughly mixed and added to the reaction vessel over 15 minutes, maintaining the reflux temperature. After the addition of Portion 4 was completed, the reaction mixture was maintained at reflux for 120 minutes and then cooled to room temperature.

The resulting graft copolymer solution had a solids content of approximately 41% by weight and had the following overall approximate composition: 30% n-butyl acrylate; 20% glycidyl methacrylate; and 50% bisomer S20W. This material had a weight average molecular weight of about 24000 and a number average molecular weight of approximately 9000.

A waterborne pigment dispersion was prepared by charging the following constituents into an 01-Attritor media mill.

Portion 1	Parts
Graft copolymer prepared above	88.72
Deionized water	208.78
Portion 2	
Quinacrodine magenta pigment	52.50
Zirconia media (0.8-1.0 mm)	850.00

The graft copolymer is mixed with deionized water to form Portion 1 (no neutralizing agent is needed). The material from Portion 1 was mixed with the materials in Portion 2 and the constituents were ground for 16 hours at 500 rpm in an 01-Attritor at 100°F. A uniform, transparent, waterborne pigment dispersion was formed that was stable and deflocculated and had a pH range of 2-4. This dispersion contains 15% pigment and 10% polymer.

- 10 This material was then encapsulated by a crosslinking reaction between epoxide groups in the backbone and a hydrophobic diamine/catalyst system.

Ingredient	Amount
Waterborne dispersion prepared above (10% polymer, 15% pigment)	20.00 g
Norbornenediamine crosslinker (amine:glycidyl methacrylate=1.0:1.0)	0.17 g
Tributyl amine	1 drop

The above constituents mixed together and heated at 40-50°C, with efficient stirring, for a period of 6 hours. After this time period, the mixture is cooled to room temperature and tested for flocculation stability as in previous examples. The encapsulated samples were tested as in Example 1 and were more stable than the non-encapsulated samples.

20 EXAMPLE 7

Two inks were prepared from unencapsulated and encapsulated dispersions and a third ink was prepared from a conventional dispersion to test the stability to thermal cycling achieved with the encapsulated dispersion as well as printability in an ink jet printing device.

25

Dispersion #1 contains a quinacridone magenta pigment and a dispersant of the type prepared in Example 1, the dispersion was prepared using a two roll mill process and was let down into water to 15% by weight pigment and 2.5 parts

- pigment to 1 part dispersant. Dispersion #2 is dispersion #1 encapsulated using the process described in Example 1. Dispersion #3 uses a conventional methacrylic dispersant and a quiniacridone magenta pigment and was prepared using a two roll mill process and was let down into water to 15% pigment and
- 5 1.5 parts pigment to 1 part dispersant. Vehicle #1 contains 100 grams of an ethoxylated glycerol, 100 grams of 1,2 hexane diol, 100 grams of diethylene glycol, 27 grams of sodium dioctyl sulfosuccinate and the balance water to a total weight of 1000 grams.
- 10 Ink #1 was prepared by adding 11 grams of dispersion #1, 25 grams of vehicle #1 and the balance water to a total of 50 grams. Ink #2 was prepared by adding 11 grams of dispersion #2, 25 grams of vehicle #1 and the balance water to a total of 50 grams. Ink #3 was prepared by adding 11 grams of dispersion #3, 25 grams of vehicle #1 and the balance water to a total of 50 grams.
- 15 The inks were then tested in an ink jet printer and all printed well. The inks were also subjected to four freeze - thaw cycles from -20°C to 60°C and the change in particle size was observed. While all inks showed an increase in average particle size, the encapsulated sample (Ink #2) increased in size by about 25% versus the
- 20 187% increase for Ink #1 and 132% increase for Ink #3. This data indicates that Ink#2 would be more stable to thermal cycling.

EXAMPLE 8

- A tint suitable for use in manufacture of paint was prepared to demonstrate the
- 25 utility of the present invention in such a process. Following the process of Example 1, a dispersion containing copper phthalocyanine blue pigment was prepared, ground and encapsulated. The resulting dispersion was then adjusted to a pH of 9 and the appearance of the dispersion drawdown (i.e., color and haze), and the percentage of solids, were compared to a standard sample.
- 30 Following the standardization of the dispersion, it was mixed with a base coat latex, water, a thickener and a biocide. The final solution pH, tinting strength and viscosity were monitored and additional water and/or thickener added to maintain standard viscosity and tint strength.

What Is Claimed Is:

1. A dispersion of particles in a liquid vehicle, comprising:
 - (a) a liquid vehicle selected from the group consisting water, organic solvents and combinations thereof;
 - 5 (b) particles that are at least substantially insoluble in the liquid vehicle;
 - (c) a polymer dispersant having at least one segment soluble in the liquid vehicle and at least one segment insoluble in the liquid vehicle,
 - 10 (d) wherein said at least one insoluble segment has cross-linking moieties that are cross-linked to at least one cross-linkable component which is insoluble in the liquid medium and is selected from the group consisting of itself, a polyfunctional monomer, a polyfunctional oligomer, and a polyfunctional polymer to form a
 - 15 encapsulation network which entraps the particles.
2. The dispersion of claim 1, wherein the vehicle comprises at least 50% water by weight.
3. The dispersion of claim 1, wherein the particle comprises a pigment.
4. The dispersion of claim 1, wherein the cross-linkable moieties on the at
20 least one insoluble segment of the polymer comprise hydroxide groups and wherein the dispersion further comprises a diisocyanate as a cross-linkable component.
5. The dispersion of claim 1, further comprising a cross-linkable component having a cross-linking moiety selected from the group consisting of amine,
25 anhydride, acid, phenolic hydroxide, hydroxyl, N-methylol, aldehyde, acetoacetoxy, isocyanate, epoxide, ester, isocyanate, radical initiator, aldehyde, activated allyl and water.
6. The dispersion of claim 1, wherein the cross-linkable moieties on the at
30 least one insoluble segment of the polymeric dispersant are selected from the group consisting of epoxy, hydroxyl, anhydride, acid, cyclic carbonate, activated allyl, amine, silane, silicate, silanol, silicone and imine.
7. The dispersion of claim 1, further comprising a catalyst to facilitate cross-linking.
8. The dispersion of claim 7, wherein said catalysts is selected from the
35 group consisting of 2,2,2-diaminobicyclooctane, dibutyltin dilaurate, tributyl amine, trioctyl amine, tridodecyl amine and dimethyldodecyl amine.

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C09D11/00 C09D17/00 B01F17/00		International Application No PCT/US 99/23193
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 C09D B01F C09B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 540 757 A (SEIKO EPSON CORP) 12 May 1993 (1993-05-12) page 4, line 15-50 page 5, line 34-54 page 5, line 55 -page 6, line 15 ---	1
A	EP 0 722 994 A (LEXMARK INT INC) 24 July 1996 (1996-07-24) page 3, line 1 -page 5, line 22 page 5, line 23-32 page 5, line 33-43 ---	1
A	EP 0 340 976 A (PPG INDUSTRIES INC) 8 November 1989 (1989-11-08) -----	
<input type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents :		
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search 1 February 2000	Date of mailing of the international search report 08/02/2000	
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl. Fax: (+31-70) 340-3016	Authorized officer Miller, A	

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 99/23193

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0540757 A	12-05-1993	DE 69221425 D	11-09-1997
		DE 69221425 T	26-02-1998
		US 5607999 A	04-03-1997
		WO 9220749 A	26-11-1992
		SG 49115 A	18-05-1998
EP 0722994 A	24-07-1996	US 5589522 A	31-12-1996
		BR 9505978 A	23-12-1997
		CA 2164553 A	22-06-1996
		DE 69510026 D	08-07-1999
		DE 69510026 T	23-12-1999
EP 0340976 A	08-11-1989	JP 8231912 A	10-09-1996
		US 4910249 A	20-03-1990
		AU 615290 B	26-09-1991
		AU 3377789 A	14-12-1989
		CA 1333738 A	27-12-1994
		CN 1037522 A	29-11-1989
		DE 68923216 D	03-08-1995
		DE 68923216 T	07-03-1996
		DK 212589 A	03-11-1989
		ES 2076956 T	16-11-1995
		JP 9227751 A	02-09-1997
		JP 2016110 A	19-01-1990
		JP 2655574 B	24-09-1997
		NO 891757 A	03-11-1989
		US 5098974 A	24-03-1992